

Technical Data Pipes Conforming to ASTM A-53* Gr. A & B Sch. 20/40/80										
Nominal Bore		Outside Diameter		Schedule	Wall Thickness		Weight Of Black Pipes Plain End			No. of pcs per Bundle
mm	inch	mm	inch		mm	inch	Kg/mtr	lbs/ft.	ft/ton	
15	1/2	21.3	0.84	40	2.77	0.109	1.27	0.85	2592	120
				80	3.73	0.147	1.62	1.09	20230	
20	1/4	26.7	1.05	40	2.87	0.113	1.69	1.13	1945	90
				80	3.91	0.154	2.2	1.48	1490	
25	1	33.4	1.315	40	3.38	0.133	2.5	1.68	1311	60
				80	4.55	0.179	3.24	2.17	1016	
32	1 1/4	42.2	1.66	40	3.56	0.14	3.39	2.27	967	42
				80	4.85	0.191	4.47	3	735	
40	1 1/2	48.3	1.9	40	3.68	0.145	4.05	2.72	810	36
				80	5.08	0.2	5.41	3.63	607	
50	2	60.3	2.375	40	3.91	0.154	5.44	3.66	603	26
				80	5.54	0.218	7.48	5.03	438	
65	2 1/2	73	2.875	40	5.16	0.203	8.63	5.8	380	18
				80	7.01	0.276	11.41	7.67	287	
80	3	88.9	3.5	40	5.49	0.216	11.29	7.58	291	14
				80	7.62	0.3	15.27	10.26	215	
90	3 1/2	101.6	4	40	5.74	0.226	13.57	9.12	242	12
				80	8.08	0.318	18.63	12.52	176	
100	4	114.3	4.5	40	6.02	0.237	16.07	10.8	204	10
				80	8.56	0.337	22.32	15	147	
125	5	141.3	5.56	40	6.55	0.258	21.77	14.63	151	8
150	6	168.3	6.625	40	7.11	0.28	28.26	18.99	116	7
200	8	219.1	8.625	20	6.35	0.25	33.31	22.38	98	5
				30	7.04	0.277	36.31	24.72	89	3
				40	8.18	0.322	42.55	28.58	77	3
250	10	273	10.748	20	6.35	0.25	41.75	28.06	79	3
				30	7.8	0.307	51.01	34.27	64	3
				40	9.27	0.365	60.29	40.52	54	3
300	12	323.8	12.748	20	6.35	0.25	49.71	33.41	66	3
				30	8.38	0.33	65.18	43.1	50	3
				40	9.52	0.375	73.78	49.61	44	3
350	14	355.6	14	10	6.35	0.25	54.69	36.75	60	3
				20	7.92	0.312	67.9	45.65	48	3
				30	9.52	0.375	81.25	54.62	40	3